



UNITED STATES DEPARTMENT OF COMMERCE
Patent and Trademark Office

Address: COMMISSIONER OF PATENTS AND TRADEMARKS
Washington, D.C. 20231

MS

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.
09/355,987	11/18/99	BARRESI	J 6224/JCK

IM22/1130

MILES & STOCKBRIDGE P.C.
1751 PINNACLE DRIVE, SUITE 500
MCLEAN VA 22102-3833

EXAMINER

COMBS, J

ART UNIT	PAPER NUMBER
----------	--------------

1742

DATE MAILED: 11/30/00

11

Please find below and/or attached an Office communication concerning this application or proceeding.

Commissioner of Patents and Trademarks

Office Action Summary

Application No.
09/355,987

Applicant(s)
Barresi et al.

Examiner
Janelle Combs Morillo

Group Art Unit
1742



☒ Responsive to communication(s) filed on Sep 22, 2000

☒ This action is **FINAL**.

☐ Since this application is in condition for allowance except for formal matters, **prosecution as to the merits is closed** in accordance with the practice under *Ex parte Quayle*, 35 C.D. 11; 453 O.G. 213.

A shortened statutory period for response to this action is set to expire 3 month(s), or thirty days, whichever is longer, from the mailing date of this communication. Failure to respond within the period for response will cause the application to become abandoned. (35 U.S.C. § 133). Extensions of time may be obtained under the provisions of 37 CFR 1.136(a).

Disposition of Claim

- ☒ Claim(s) 1-20 is/are pending in the application.
- Of the above, claim(s) _____ is/are withdrawn from consideration.
- ☐ Claim(s) _____ is/are allowed.
- ☒ Claim(s) 1-20 is/are rejected.
- ☐ Claim(s) _____ is/are objected to.
- ☐ Claims _____ are subject to restriction or election requirement.

Application Papers

- ☐ See the attached Notice of Draftsperson's Patent Drawing Review, PTO-948.
- ☐ The drawing(s) filed on _____ is/are objected to by the Examiner.
- ☐ The proposed drawing correction, filed on _____ is ☐ approved ☐ disapproved.
- ☐ The specification is objected to by the Examiner.
- ☐ The oath or declaration is objected to by the Examiner.

Priority under 35 U.S.C. § 119

- ☒ Acknowledgement is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d).
- ☒ All ☐ Some* ☒ None of the CERTIFIED copies of the priority documents have been
- ☐ received.
- ☐ received in Application No. (Series Code/Serial Number) _____.
- ☒ received in this national stage application from the International Bureau (PCT Rule 17.2(a)).

*Certified copies not received: _____

- ☐ Acknowledgement is made of a claim for domestic priority under 35 U.S.C. § 119(e).

Attachment(s)

- ☐ Notice of References Cited, PTO-892
- ☒ Information Disclosure Statement(s), PTO-1449, Paper No(s). 7 and 9
- ☐ Interview Summary, PTO-413
- ☐ Notice of Draftsperson's Patent Drawing Review, PTO-948
- ☐ Notice of Informal Patent Application, PTO-152

--- SEE OFFICE ACTION ON THE FOLLOWING PAGES ---

Art Unit: 1742

DETAILED ACTION

Claim Rejections - 35 USC § 103

1. The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all obviousness rejections set forth in this Office action:

(a) A patent may not be obtained though the invention is not identically disclosed or described as set forth in section 102 of this title, if the differences between the subject matter sought to be patented and the prior art are such that the subject matter as a whole would have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter pertains. Patentability shall not be negated by the manner in which the invention was made.

2. Claims 1-20 are rejected under 35 U.S.C. 103(a) as being unpatentable over the ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials.

The ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials teaches that cast aluminum alloy 356.0 has a composition comprising: 0.20-0.45% Mg, 6.5-7.5% Si, and 0.6% max. Fe (page 164), which overlaps the composition as presently claimed in claims 1, 4, 5, and 15. Said alloy is typically solution heat treated at 535-540°C for 8-12 hours, quenched in hot water (~ 65-100°C), and aged at 150-230°C for 2-9 hours (Table 36, page 168), which are substantially the same process steps as presently claimed in claims 12, 13, 14, 19, 20.

The ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials teaches that cast aluminum alloy 357.0 has a composition comprising: 0.45-0.6% Mg, 6.5-7.5% Si, and 0.15% max. Fe (page 166), which overlaps (or touches the boundary) of the composition as presently claimed in claims 1, 4, 5, and 15. Said alloy is typically solution heat treated at 540°C for 8 hours, hot water quenched, followed by aging ~ 170°C for 3-5 hours

Art Unit: 1742

(page 166), which are substantially the same process steps as presently claimed in claims 12, 13, 14, 19, 20.

The prior art does not teach the solidification rate of the casting or what phases are present as the result of the above mentioned process steps. The examiner asserts that it is well known to one of ordinary skill in the art to solidify castings at rapid rates in order to produce a high quality casting with small DAS, as shown by the ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials on page 133. Therefore, it would have been obvious to one of ordinary skill in the art to solidify said aluminum casting at “intermediate” to “high” (as defined in the specification page 9 lines 8-18) solidification rates in order to produce a high quality casting with small DAS. The prior art does not teach what phases are present in the final (and intermediate) aluminum alloy processed as stated above. However, the present specification states that “solution treatment at 540°C for 2 or more hours produced desired levels of transformation of π to β phase” (page 8 lines 13-15), which is substantially the same as the solution heat treatment steps of the prior art. The examiner asserts that because the prior art discloses substantially the same aluminum alloy processed in substantially the same steps, substantially the same product would result as presently claimed. Absent evidence to the contrary, it is held the ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials has created a prima facie case of obviousness of the presently claimed invention.

Art Unit: 1742

3. Claims 1-20 are rejected under 35 U.S.C. 103(a) as being unpatentable over JA 53-16312 in view of the ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials.

JA 53-16312 teaches an aluminum alloy comprising 6-8% Si, 0.2-0.4% Mg, and 0.001-0.15% Fe, which overlaps (or touches the boundary) of the composition as presently claimed in claims 1, 4, 5, and 15. Said alloy is processed through the steps comprising: casting, solution heat treating 545-555°C for about 9 hours, quenching in 70°C hot water, and aging at ~130°C for 4 hours (see abstract), which are substantially the same process steps as presently claimed in claims 12, 13, 14, 19, 20.

The prior art of JA 53-16312 does not teach the solidification rate of the casting or what phases are present as the result of the above mentioned process steps. However, the ASM Handbook: Vol. 2 Properties and Selection: Nonferrous Alloys and Special-Purpose Materials, as stated above, teaches the solidification of castings at rapid rates in order to produce high quality castings with small DAS (p 133). The prior art does not teach what phases are present in the final (and intermediate) aluminum alloy processed as stated above. However, the present specification states that "solution treatment at 540°C for 2 or more hours produced desired levels of transformation of π to β phase" (page 8 lines 13-15), which is substantially the same as the solution heat treatment steps of the prior art.

Therefore, it would have been obvious to one of ordinary skill in the art to solidify said aluminum casting (of composition given by JA 53-16312 or ASM Handbook: Vol. 2) at

Art Unit: 1742

“intermediate” to “high” (as defined in the specification page 9 lines 8-18) solidification rates in order to produce a high quality casting with small DAS, as taught by ASM Handbook: Vol. 2.

The examiner asserts that because the prior art discloses substantially the same aluminum alloy processed in substantially the same steps, substantially the same product would result as presently claimed.

Response to Arguments

4. In the response filed September 22, 2000 the applicant has added an abstract, and overcome the objection to the specification. The argument that the solution heat-treatment as presently claimed is not the same as the prior art, has not been found persuasive. The presently claimed solution heat treatment procedure overlaps the prior art solution heat treatment procedures (see rejections, above). The argument that the composition ranges of GB'531 are outside the presently claimed composition ranges has been found persuasive, and the rejections over GB'531 have been withdrawn. The argument that there is no motivation in the prior art to enable one of skill in the art to set out to form the 356.0 and 357.0 alloys, wherein the sole or predominant Fe-containing phase is β which forms as a transformation product of the π phase has not been found persuasive. The examiner points out that because the prior art performs substantially the same process on substantially the same alloy composition, substantially the same results would occur, absent evidence to the contrary. The argument that the prior art does not recognize that limiting the π phase improves mechanical properties has not been found

Art Unit: 1742

persuasive. The applicant states in the present specification that the π phase has a negative impact on both ductility and strength. However, the applicant has not shown that the present invention achieves improved ductility and strength as compared to the prior art of record.

Conclusion

5. **THIS ACTION IS MADE FINAL.** Applicant is reminded of the extension of time policy as set forth in 37 CFR 1.136(a).


A shortened statutory period for reply to this final action is set to expire THREE MONTHS from the mailing date of this action. In the event a first reply is filed within TWO MONTHS of the mailing date of this final action and the advisory action is not mailed until after the end of the THREE-MONTH shortened statutory period, then the shortened statutory period will expire on the date the advisory action is mailed, and any extension fee pursuant to 37 CFR 1.136(a) will be calculated from the mailing date of the advisory action. In no event, however, will the statutory period for reply expire later than SIX MONTHS from the mailing date of this final action.


6. Any inquiry concerning this communication or earlier communications from the examiner should be directed to Janelle Combs- Morillo whose telephone number is (703) 308-4757. The examiner can normally be reached Monday through Friday from 7:30am to 5:00pm.

Art Unit: 1742

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Roy King, can be reached on (703) 308-1146. The fax phone number for the organization where this application or proceeding is assigned is (703) 305-7719.

Any inquiry of a general nature or relating to the status of this application or proceeding should be directed to the receptionist whose telephone number is (703) 308-0661.


GEORGE WYSZOMIERSKI
PRIMARY EXAMINER

jcm 

November 29, 2000